



Typical Properties

PU11092

85°A unfilled general purpose cast elastomer suitable for industrial environments

| Property | Test Method | Value | SI Units | Value | Imp Units |
|----------------------------------|--------------------|--------------|-----------------|--------------|---------------------|
| Color | - | Blaze Orange | - | - | - |
| Shore Hardness | Shore A | 85 ° | A | 85 ° | A |
| Tensile Strength | ASTM D412 | 26 | MPa | 3770 | lbf/in ² |
| Elongation @ Break | ASTM D412 | 490 | % | 490 | % |
| Nicked Crescent Tear Strength | ASTM D624 | 78 | N/mm | 442 | lb/in |

Author S. Kotrulja Issue No 00

Approved By S. Kotrulja Date of Approval/Issue 8 Feb 10